

Technical Data Sheet

Prusament PC Blend Carbon Fiber by Prusa Polymers

Identification:

Trade name	Prusament PC Blend Carbon Fiber
Chemical name	Polycarbonate blend filled with Carbon Fiber
Usage	FDM/FFF 3D printing
Diameter	1,75 ± 0,04 mm
Manufacturer	Prusa Polymers a.s., Prague, Czech Republic

Recommended print settings:

Nozzle Temperature [°C]	285 ± 10
Heatbed Temperature [°C]	110 ± 10
Print Speed [mm/s]	up to 200
Cooling Fan Speed [%]	0 % (0 - 20 %*)
Brim	Not necessary in general

*Depends on the geometry of the printed object, to improve bridges set 20 % in PrusaSlicer. Note, cooling decreases significantly interlayer adhesion with just small or no effect on printing quality.

Typical material properties:

	Typical Value	Method
MFR [g/10min]⁽¹⁾	18	ISO 1133
MVR [cm³/10min]⁽¹⁾	16	ISO 1133
Density [g/cm³]	1,16	Prusa Polymers
Moisture Absorption 24 hours [%]⁽²⁾	0,38	Prusa Polymers
Moisture Absorption 7 days [%]⁽²⁾	0,42	Prusa Polymers
Heat Deflection Temperature (0,45 MPa) [°C]	114	ISO 75
Heat Deflection Temperature (1,80 MPa) [°C]	106	ISO 75
Tensile Yield Strength Filament [MPa]	55 ± 2	ISO 527
Hardness - Shore D	82	Prusa Polymers
Interlayer adhesion [MPa]	20 ± 2	Prusa Polymers

(1) 265 °C; 5 kg

(2) 25 °C; humidity 23 %

Mechanical properties of printed testing specimens⁽³⁾:

Property\Print Direction	Horizontal	Vertical xz	Method
Tensile Yield Strength [MPa]	55 ± 4	65 ± 4	ISO 527-1
Tensile Modulus [GPa]	2,3 ± 0,1	2,8 ± 1	ISO 527-1
Elongation at Yield Point [%]	3,5 ± 0,5	3,9 ± 0,4	ISO 527-1
Flexural Strength [MPa]	85 ± 1	106 ± 1	ISO 178
Flexural Modulus [GPa]	3,0 ± 0,1	4,9 ± 0,1	ISO 178
Deflection at Flexural Str. [mm]	8,8 ± 0,2	6,9 ± 0,1	ISO 178
Impact Strength Charpy ⁽⁴⁾ [kJ/m ²]	30 ± 6	35 ± 3	ISO 179-1
Impact S.Charpy notch. ⁽⁵⁾ [kJ/m ²]	9 ± 1	10 ± 1	ISO 179-1

(3) Original Prusa i3 MK3S 3D printer was used to make testing specimens. PrusaSlicer-2.3.1 was used to create G-codes with following settings: Prusament PC Blend Carbon Fiber; Print settings 0,20 mm FAST (layers 0,2 mm); solid layers Top: 0 Bottom: 0; perimeters: 2, infill 100 % Rectilinear, infill print speed 200 mm/s; extruder temperature 285 °C all layers; bed temperature 120 °C all layers; extrusion multiplier 1,07; print cooling off; other parameters set default

(4) Charpy unnotched - Edgewise direction of blow according to ISO 179-1

(5) Charpy notched - Edgewise direction of blow according to ISO 179-1

Disclaimer:

The results presented in this data sheet are just for your information and comparison. Values are significantly dependent on print settings, the operator's experience, and surrounding conditions. Everyone has to consider suitability and possible consequences of printed parts usage. Prusa Polymers a.s. can not carry any responsibility for injuries or any loss caused by using Prusament PC Blend CF (Prusament PC Blend Carbon Fiber) material. Before using PC Blend material read properly all the details in the available safety data sheet (SDS).

